



TIKKURILA  
**PRESTO LH**  
LIGHT FILLER

**DESCRIPTION** Water-borne, ready to use light filler. Filling ability 4 mm with no cracking. Minimal shrinkage and good adhesion.

**RECOMMENDED USES** Interior walls and ceilings on dry premises.

**PRODUCT FEATURES** Particularly suitable for leveling gray substrates, such as gypsum board, concrete, light-weight concrete and rendered surfaces, but also for chipboard and woodfiber board surfaces. Also ideal for smoothing the joints between gypsum boards.





## PRESTO LH

### TECHNICAL DATA

<b>Colour Shades</b>	Gray
<b>Can sizes</b>	3 l, 10 l
<b>Application method</b>	Apply with a smoothing trowel.
<b>Drying time (23°C and 50% relative air humidity)</b>	The surface can be sanded and painted in 2–24 hours, depending on the layer thickness, temperature and relative humidity of the air.
<b>Density (kg/l)</b>	1.1 kg/l, ISO 2811
<b>Shrinkage</b>	Minimal.
<b>Volume solids (%)</b>	59
<b>Special feature</b>	The light filling material used in this filler makes it light and easy to apply.
<b>Storage</b>	Protect from frost. Badly closed or short cans endure badly long-time storage.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



# PRESTO LH

## APPLICATION INSTRUCTIONS

### Application conditions

The surface to be treated must be dry. The minimum ambient temperature for use of the product is +10 °C and maximum relative air humidity 80%.

### Surface preparation

Unpainted surfaces:

Clean the surfaces of dirt. Remove any dust and loose material by brushing.

Previously painted surfaces:

Wash previously painted surfaces with Maalipesu cleaning agent. Remove as much paint as you can with a scraper and sand painted surfaces to a matte finish. Remove the sanding dust.

### Application

Apply Presto Kevytasoite LH with a smoothing trowel. Sand the dried surface and remove sanding dust. Apply another coat of filling if necessary.

### Cleaning of tools

Clean tools with water.

### Environmental and waste disposal


Deliver empty packaging and hardened mortar to a recycling point or waste tip according to local regulations.

## HEALTH AND SAFETY LABELLING according to Regulation (EC) No. 1272/2008

Contains 1,2-benzisothiazol-3(2H)-one (BIT) and reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)). May produce an allergic reaction. Wear protective gloves. This product contains a biocidal product for the preservation of the product during storage. Contains: reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one [EC no. 220-239-6] (3:1) (C(M)IT/MIT (3:1)).

# PRESTO LH


EN 13963:2005

	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
TIK-1650-5002a	
EN 13963:2005	
Jointing material of gypsum plasterboards - Type 2A.	
Reaction to fire	A2-s1,d0
Flexural strength	> 320 N
Release of dangerous substances	NPD

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

# PRESTO LH

EN 15824:2009

	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
TIK-1650-5002b	
EN 15824:2009	
Internal plaster based on organic binder.	
Reaction to fire	B-s1,d0
Adhesion strength by pull off test	≥ 0,3 MPa
Release of dangerous substances	NPD

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.