



TIKKURILA
PRESTO LF
RENOVATION FILLER

DESCRIPTION Water-borne, ready to use renovation filler. Filling ability 4 mm with no cracking. Minimal shrinkage and good adhesion.

RECOMMENDED USES Interior walls and ceilings on dry premises.

PRODUCT FEATURES Particularly suitable for the full or partial leveling of previously painted surfaces. For filling holes and seams and attaching sealing strips. Suitable for gypsum board, woodfiber board, concrete and rendered surfaces.





PRESTO LF

TECHNICAL DATA

Colour Shades	Near to white
Can sizes	0.2 l, 0.4 l, 3 l, 10 l
Application method	Apply with a smoothing trowel.
Drying time (23°C and 50% relative air humidity)	The surface can be sanded and painted after the filler has dried completely (under normal conditions in 2–24 hours, depending on the layer thickness, temperature and relative humidity of the air).
Density (kg/l)	1.2 kg/l, ISO 2811
Shrinkage	Minimal.
Volume solids (%)	61
Grain size	max. 0,15 mm
Storage	Protect from frost. Badly closed or short cans endure badly long-time storage.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.



PRESTO LF

APPLICATION INSTRUCTIONS

Application conditions

The surface to be treated must be dry. The minimum ambient temperature for use of the product is +10 °C and maximum relative air humidity 80%.

Surface preparation

Unpainted surfaces:

Clean the surfaces by removing any grease and dirt. Remove any dust and loose material by brushing.

Previously painted surfaces:

Wash previously painted surfaces with Maalipesu cleaning agent. Let the surface dry before further treatment. Remove as much paint as you can with a scraper and sand painted surfaces to a matte finish. Remove the sanding dust.

Application

Apply Presto LF Remonttiasoitte with a smoothing trowel. Sand the dried surface and remove sanding dust. Apply another coat of filling if necessary.

Joint sealing

Spread the filler over the joint with a smoothing trowel. Immediately press the sealing strip into the wet filler with a smoothing trowel. Spread the filler over the sealing strip. Sand the dried surface and remove the sanding dust.

Cleaning of tools

Clean tools with water.

Environmental and waste disposal


Deliver empty packaging and hardened mortar to a recycling point or waste tip according to local regulations.

HEALTH AND SAFETY LABELLING according to Regulation (EC) No. 1272/2008

Contains 1,2-benzisothiazol-3(2H)-one (BIT). May produce an allergic reaction. Wear protective gloves.

PRESTO LF


EN 13963:2005

	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
TIK-1650-5003a	
EN 13963:2005	
Jointing material of gypsum plasterboards - Type 3A.	
Reaction to fire	A2-s1,d0
Flexural strength	> 320 N
Release of dangerous substances	NPD

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

PRESTO LF

EN 15824:2009

	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
TIK-1650-5003b	
EN 15824:2009	
Internal plaster based on organic binder.	
Reaction to fire	B-s1, d0
Adhesion strength by pull off test	≥ 0,3 MPa
Release of dangerous substances	NPD

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.