



# Temafloor P300

## DESCRIPTION

A two-component, solvent-free epoxy coating.

## PRODUCT FEATURES AND RECOMMENDED USES

- Good resistance to abrasion
- Withstands water, oils, greases, chemicals and dilute solutions of non-oxidizing acids, alkali and salt solutions. Resists only temporary splashes of oxidizing acids and bleaching chemicals. A separate chemical resistance table available
- Withstands +70°C dry heat and +60°C in immersion. Does not resist abrupt, great or repeated changes of temperature
- Self-levelling coating
- Temafloor Flex hardener makes the paint surface flexible and thus more resistant to cracking of concrete
- Also RAL EFFECT metallic colour shades are available
- For new and old concrete floors exposed to heavy mechanical and chemical stress in industrial and storage facilities, repair shops; e.g. process or paper machine units and corridors. Also for car parks, garages, business premises, shopping centres, restaurants and cafe's

## TECHNICAL DATA

### Volume solids

approx. 100%

### Specific gravity

1.4 kg / l (mixture).

### Mixing ratio

Base	4 parts by volume	Temafloor P300
Hardener	1 part by volume	008 4514
or		
Paint	2 parts by volume	Temafloor P300
FLEX hardener	1 part by volume	930 5002

### Pot life (+23°C)

20–30 minutes on substrate, approx. 15 minutes in the mixing container.

### Practical coverage

Coverage on concrete floors is on the average:  
Film thickness 0.3 mm coverage approx. 3 m<sup>2</sup>/litre  
Film thickness 0.5 mm coverage approx. 2 m<sup>2</sup>/litre  
Practical coverage depends on the porosity and evenness of the substrate and on the application method.

### Drying time (+23°C)

Dust dry after 6 hours  
Light trucking after 16 hours  
Fully cured after 7 days  
At lower temperature the curing process will last longer. With Temafloor FLEX hardener the curing times are a little longer than with standard hardener.

### Cleaning of equipment

Thinner 1029 or 1031.

### Finish

Full gloss.

### Colors

RAL, NCS, SSG, BS, MONICOLOR NOVA and SYMPHONY colour cards. Temaspeed Premium tinting. Also metallic shades are available

### Thinning instructions

Do not thin Temafloor P 300 epoxy coating.

### Reaction to fire

B<sub>FL</sub>-s1 according to standard EN 13501-1.

### VOC

VOC 2004/42/EC (cat A/j) 500 g/l (2010)  
Temafloor P300: max. VOC < 500 g/l

### Can sizes

3,0 L, 10,0 L, 20,0 L, 200,0 L

# Temafloor P300

## APPLICATION INSTRUCTIONS

- Surface preparation**
- New concrete: Remove laitance by power grinding, vacuum grit blasting or hydrochloric acid etching. Choose the method best suited for the premises. After grinding remove dust carefully with a vacuum cleaner. Hydrochloric acid etching is carried out with diluted hydrochloric acid (1 part concentrated hydrochloric acid, 4 parts water). Rinse with plenty of water. Dry the floor.
- Old concrete: Remove all grease, oil, chemicals and other impurities by Maalipesu detergent. Remove old peeling paint layer by grinding or vacuum grit blasting. Choose the method best suited for the premises. Clean out pot-holes removing all loose friable material. Open cracks with e.g. an abrasive tool. Remove loose material and dust.
- If cementitious screed is used, check compatibility with the levelling screed manufacturer.
- Application conditions**
- The relative humidity of the concrete should not exceed 97%. The temperature of the ambient air, surface or coating should not fall below +15°C during application or drying. Relative humidity of air should not exceed 80%.
- Note! There is a natural tendency of this coating to chalk, discolor or yellow unevenly. It is recommended to use polyurethane topcoat when there are high aesthetical requirements on color appearance.
- Mixing components**
- First stir base and hardener separately. Mix the correct proportions of base and hardener thoroughly (approx. 2 minutes to get homogenous mixture) by using a low speed industrial hand drill with a paddle. Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface, weaken the properties of the coating and risk the success of the application.
- Priming**
- Prime using Temafloor 200, Temafloor 400 or Temafloor 220W epoxy varnish thinned 20–50% with Thinner 1029 or Fontefloor EP Primer epoxy varnish thinned 20–50% with water. Pour the varnish mixture onto the floor and apply as much as is needed to impregnate the concrete surface. If necessary, repeat priming to get a non-porous surface. A porous priming coat will result in holes and air bubbles in the finished coating. Subsequent treatment can be carried out after 2 hours using "wet-on-wet" technique.
- Patching**
- Patch pot-holes and cracks with Colofill putty or a mixture of unthinned Temafloor 200 Primer epoxy varnish or Temafloor P 300 epoxy coating and dry, clean sand. Mixing ratio e.g. 1 part by volume of varnish mixture and 1–2 parts by volume of sand of grain size 0.1–0.6 mm. Sand the patched areas before overcoating, if necessary.
- Note! Concrete surface should always be primed before patching.
- Topcoating**
- Overcoating should be done within 6–24 hrs after priming with unthinned Temafloor P300. If the primed surface is not overcoated within 24 hrs, it should be abraded. Pour the mixture onto the floor and apply it with a trowel and level with a roller.
- Control that the thickness of layer is correct by observing coating consumption and by measuring the film thickness. Recommended film thickness is 0.3–0.5 mm. It is recommended to apply two thin layers with minimum DFT 0.3 mm. Use spiked roller to finish the surface approx. 10–20 min after application. Spiked roller helps removing air bubbles from the coating.
- Temafloor P300 metallic shades can be applied with a brush, roller or airless spray. Using a roller with different colour shades produces a vivid surface with a metallic shine effect. Recommended film thickness is 0.5–1.0 mm.



## Temafloor P300

### HEALTH AND SAFETY

Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.

A health and safety data sheet is available on request from Tikkurila Oyj.

### **For industrial and professional use only.**

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.


In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.

# Temafloor P300

## EN 13813

The European harmonized productstandard EN 13813:2002 defines the requirements for Screed materials and floor screeds, including synthetic resin screeds.

This product is tested and CE-labelled in accordance with the tables ZA.1.5 and ZA.3.3 in the appendix ZA.3.


	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 VANTAA	
11	
TIK-0167-5001b	
EN 13813 SR-RWA1-B2,0-IR4	
Synthetic resin screed.	
Impact resistance	IR4
Capillary absorption and permeability to water	$w < 0,1 \text{ kg/m}^2 \cdot \text{h}^{0,5}$
Chemical resistance	CR 1, 2, 4...5, 8, 11...14, 15a (Class 2)
Release of corrosive substances	SR
Abrasion resistance	RWA 1
Thermal resistance	NPD
Reaction to fire	B <sub>ff</sub> -s1
Adhesion strength by pull off test	B 2.0
Release of dangerous substances	NPD
Sound absorption	NPD
Sound insulation	NPD

# Temafloor P300

## EN 1504-2:2004

The European harmonized productstandard EN 1504-2:2004 defines the requirements for surface protection systems for concrete.

This product is tested and CE-labelled in accordance with the tables 1d, 1f and 1g in the appendix ZA.

	
0809	
Tikkurila Oyj Kuninkaalantie 1 FI-01300 Vantaa	
13	
0809-CPD-0773	
TIK-0167-5001a	
EN 1504-2:2004	
Product for protection and repair of concrete structures – Coating.	
Permeability to CO2	$s_D > 50 \text{ m}$
Impact resistance	Class I: $\geq 4 \text{ Nm}$
Capillary absorption and permeability to water	$w < 0,1 \text{ kg/m}^2 \cdot \text{h}^{0,5}$
Abrasion resistance	$< 3000 \text{ mg}$
Reaction to fire	$B_{fl-s1}$
Adhesion strength by pull off test	$\geq 2,0 \text{ N/mm}^2$
Release of dangerous substances	NPD
Permeability to water vapour	Class II, $5 \text{ m} < s_D < 50 \text{ m}$
Resistance to severe chemical attack	Class II