



Pinja EP

DESCRIPTION

Waterborne acrylic – latex paint.

PRODUCT FEATURES AND RECOMMENDED USES

- Forms a flexible coating with low water permeability
- Recommended for painting the outer edge of the wooden surfaces, wood, plywood, chipboard, OSB

TECHNICAL DATA

Volume solids

Approx. 35 % volume (depending on colour).

Weight solids

Approx. 42 % weight (depending on colour).

Recommended spreading amounts and theoretical coverage

8-10 m²/l per one coat (100-120 g/m² on wet). Practical coverage depends on: the conditions, application method, painting tool used, the color and texture and absorbency of the substrate.

Drying times

In temperature +23°C, relative air humidity of 50%, dry touch 0,5 - 1 hour. Recoatable after 0,5 - 1 hour. Drying times and repainting depend on the thickness, surface, temperature, humidity and ventilation.

Gloss

Semi-matt.

Color shades

Tinting in Tikkurila AVATINT system.



Pinja EP

APPLICATION INSTRUCTIONS

- Application conditions** During the application and drying the temperature of the surface should be at least 5°C and relative air humidity should not exceed 80%. In confined spaces require good ventilation during application and drying.
- Application** Stir the paint thoroughly before painting. If necessary, diluted with water to 5%.
At airless spray application the product can be diluted to a required viscosity. Spray nozzle airless 0.013"- 0.015" and nozzle pressure 40-120Bar pressure spray 1-3Bar.
- Cleaning of equipment** Water, Tikkurila Akvi Thinner. Before cleaning tools should be thoroughly dried in order to remove as much paint. Clean tools with water immediately after work.
- VOC** Produkt zawiera poniżej 10 g/l LZO.

- HEALTH AND SAFETY** Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.
A health and safety data sheet is available on request from Tikkurila Oyj.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.