



Fontecryl AP

DESCRIPTION

A water-borne, one-component fast-drying acrylic based primer for various surfaces containing active anticorrosive pigments.

PRODUCT FEATURES AND RECOMMENDED USES

- Provides excellent adhesion and is used as an anti-corrosive primer on steel, aluminium and zinc surfaces
- Due to its good wetting and levelling properties, Fontecryl AP is also suitable for dipping applications
- Can be overcoated both with water and solvent-borne topcoats.
- Wide range of colors available
- Drying times can be shortened by using higher temperatures
- Recommended to be used in process industry and agriculture and earth moving equipment

TECHNICAL DATA

Volume solids 33±2% (ISO 3233).

Weight solids 45±2%

Specific gravity 1.2 kg / l

Recommended film thicknesses and theoretical coverage

Recommended film thicknesses		Theoretical coverage
wet	dry	
125µm	40µm	8.3 m ² /l
Recommended film thicknesses with Duasolid 50 as a topcoat		Theoretical coverage
wet	dry	
60µm	20µm	16.5 m ² /l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Drying time

DFT 40µm	+15°C	+23°C	+35°C
Dust dry, after	2h	30min	5min
Touch dry, after	2½h	1h	15min
Recoatable, min., after	24h	1–2 h	30min

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation

Gloss

Matt.

Color shades

RAL, NCS, SSG, BS, MONICOLOR NOVA and SYMPHONY colours made from FCL base paint. Temaspeed Fonte tinting

Fontecryl AP

APPLICATION INSTRUCTIONS

Surface preparation	<p>Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)</p> <p>Steel surfaces: Blast clean to grade Sa2½. (ISO 8501-1) If blast cleaning is not possible, phosphating is recommended for cold rolled steel to improve adhesion.</p> <p>Zinc surfaces: Sweep blast clean with mineral abrasives, e.g. quartz sand, to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with Panssaripesu detergent. For hot dip galvanized surfaces see separate application instructions or contact Tikkurila Technical Service.</p> <p>Aluminium surfaces: Sweep blast clean with non-metallic abrasives to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with Maalipesu detergent.</p>
Recommended primers	Fontecryl AP.
Recommended topcoats	Duasolid 50, Fontedur HB 80, Fontelac QD 80, Temadur SC-F 20, Temadur SC-F 50, Temadur SC-F 80.
Application conditions	All surfaces must be clean, dry and free from contamination. The temperature of the ambient air, surface and paint should not fall below +15°C during application and drying. Relative humidity of the air should be between 20–70%. The surface temperature of steel should remain at least 3°C above the dew point. Good ventilation and sufficient air movement is required in confined areas during application and drying.
Application	<p>For spraying, the product is thinned approximately 0–15%. Recommended nozzle tip is 0.011" – 0.015" ja pressure 120–160 bar. Spray angle shall be chosen according to the shape of the object.</p> <p>For dip coating, the product is thinned 7–15% to the viscosity 20–25s DIN 4.</p> <p>For brush application the product should be thinned according to the circumstances.</p> <p>Mix the product properly in case of sedimentation or viscosity increase.</p> <p>Note! The viscosity falls quickly when thinning the paint.</p>
Thinners	Water
Cleaning of equipment	<p>Clean the spraying equipment immediately after use as follows:</p> <ol style="list-style-type: none">1. Run the equipment with water to remove excess paint from the equipment.2. Run the equipment with a mixture of approx 20% Thinner 1109 in clean water, at least two times.3. Finally wash with undiluted Thinner 1109. <p>Wash the equipment with water before starting to paint again. Unwashed equipment can cause serious surface defects.</p>
VOC	<p>The Volatile Organic Compounds amount is 120 g/litre of paint.</p> <p>VOC content in paint (thinned 15% by volume) is 100 g/l.</p>



Fontecryl AP

HEALTH AND SAFETY

Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.

A health and safety data sheet is available on request from Tikkurila Oyj.

For industrial and professional use only.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.