

Temadur SC-F 50

DESCRIPTION

A two-component fast-drying semi-gloss polyurethane paint, containing anticorrosive pigments, hardener aliphatic isocyanate.

PRODUCT FEATURES AND RECOMMENDED USES

- Excellent weathering and abrasion resistance
- Easy to clean and non-chalking surface with good gloss and colour retention
- Recommended especially to be used as a single coat finish for agricultural and earth moving machinery and other machinery and equipment
- Also suitable to be used as a topcoat in epoxy/polyurethane systems exposed to weathering and chemical stress, e.g. storage tank exteriors, steel framework and other steel structures

TECHNICAL DATA

Volume solids 63±2% (ISO 3233)

Weight solids 77±2%

Specific gravity 1.4±0.1 kg / l (mixed)

Mixing ratio
 Base 4 parts by volume Temadur SC-F 50
 Hardener 1 part by volume 008 7640

Pot life (+23°C) app. 1 hour

Recommended film thicknesses and theoretical coverage

Recommended film thicknesses/one coat application		Theoretical coverage
wet	dry	
125µm	80µm	8.0 m ² /l
190µm	120µm	5.3 m ² /l
Recommended film thicknesses/as a topcoat		Theoretical coverage
wet	dry	
65µm	40µm	15.4 m ² /l
95µm	60µm	10.5 m ² /l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Drying time

DFT 60µm	+5°C	+10°C	+23°C	+35°C
Dust dry, after	2h	1½h	50min	30min
Touch dry, after	8h	6h	3h	2h
Recoatible, after	No limitations.			

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation. When forced drying in temperatures +50–+100°C, use flash-off time between 5–30 minutes, depending on the wet film thickness and the actual temperature.

Gloss

Semi-gloss.

Color shades

RAL, NCS, SSG, BS, MONICOLOR NOVA and SYMPHONY colour cards. Temaspeed Premium tinting

Temadur SC-F 50

APPLICATION INSTRUCTIONS

Surface preparation	<p>Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)</p> <p>Steel surfaces: Blast clean to grade Sa2½. (ISO 8501-1) If blast cleaning is not possible, phosphating is recommended for cold rolled steel to improve adhesion.</p> <p>Primed surfaces: Oil, grease, salt and dirt are removed from the surface by appropriate means. Repair any damage to the primer coat. Note the overcoating time of primer. (ISO 12944-4)</p>
Recommended primers	Temadur 20, Temacoat GPL-S Primer, Temacoat GPL-S MIO, Temabond ST 200, Temabond ST 300, Temacoat Primer, Temanyl PVB, Temazinc 77.
Recommended topcoats	Temadur 50, Temadur 90, Temadur Clear, Temadur HB 50, Temadur HB 80, Temadur HS 90, Temadur SC-F 20, Temadur SC-F 50, Temadur SC-F 80, Temathane 50, Temathane 90, Temathane PC 50, Temathane PC 80.
Application conditions	All surfaces must be clean, dry and free from contamination. The temperature of the ambient air, surface and paint should not fall below +5°C during application and drying. Relative humidity of the air should not exceed 80% during application and drying. The surface temperature of steel should remain at least 3°C above the dew point. Good ventilation and sufficient air movement is required in confined areas during application and drying.
Mixing components	First stir base and hardener separately. The correct proportions of base and hardener must be mixed thoroughly before use. Use power mixer for mixing. Insufficient mixing or incorrect mixing ratio will result in uneven drying of the surface and weaken the properties of the coating.
Application	<p>For airless spraying, the product is thinned depending on the temperature of the components and shape of the object approximately 0–15%. Recommended nozzle tip is 0.011"–0.015" and pressure 160–200 bar. Spray angle shall be chosen according to the shape of the object. In order to reach thicker coats (over 100 µm) use always "wet-in-wet" technique.</p> <p>For conventional spraying, the product is thinned approximately 10–15% to the viscosity 20–25s (DIN4). Recommended nozzle tip is 1.6–1.8 mm and pressure 3–4 bar.</p>
Thinners	Thinner 1048, Thinner 1067
Cleaning of equipment	Thinner 1067 or Thinner 1048.
VOC	<p>The Volatile Organic Compounds amount is 330 g/litre of paint.</p> <p>VOC content in paint (thinned 15% by volume) is 410 g/l.</p>
HEALTH AND SAFETY	<p>Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.</p> <p>A health and safety data sheet is available on request from Tikkurila Oyj.</p> <p>For industrial and professional use only.</p>



Temadur SC-F 50

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.