



Akvilac WF 10

DESCRIPTION

A one-component water-borne lacquer. Used together with Fontefire WF Clear provides the B-s1, d0 classification.

PRODUCT FEATURES AND RECOMMENDED USES

- Chemical-resistant top lacquer for fire-retardant interior lacquer system. Extends the usage area of fire-retardant lacquer by providing resistance to the most used household chemicals
- Levels evenly and smoothly on top of fire-retardant lacquer Fontefire WF Clear. Good levelling properties ensure the excellence of the final surface
- Fast-drying and easy-to-use lacquer. Dries fast and is therefore suitable for fast production lines. As a one-component lacquer, it is very easy to use
- The product fulfills the following fire resistance requirements: Reaction to fire. Ignitability of building products, class B-s1, d0 according to EN 13501-1:2007+A1:2009
- To be used on top of Fontefire WF Clear on interior wood surfaces in industrial application processes

TECHNICAL DATA

Volume solids 30±2%

Weight solids 32±2%

Specific gravity 1.1 kg/l

Recommended spreading amounts and theoretical coverage

Recommended spreading amounts (unthinned)		Theoretical coverage
wet	dry	
60–70 g/m ²	16–20 µm	15–18 m ² /l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Drying times

60–70 g/m ²	+23°C	+50°C
Dust dry, after	10min	5min
Touch dry, after	10–15 min	10min
Dry to sand, after	20min	15min

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Gloss Matt.

Color shades Clear.



Akvilac WF 10

APPLICATION INSTRUCTIONS

Surface preparation	Remove dust, loose particles and other impurities from the surface. Wood surfaces must be sanded with sandpaper P150–320. Sanding prior to the next application with sandpaper P240–400. All sanding dust must be removed.
Recommended primers	Fontefire WF Clear.
Application conditions	The surface to be treated has to be clean and dry. The moisture content of wood has to be below 20%. During application and drying temperature of the air, substrate and paint must be over +18°C and relative humidity of the air below 70%. Good ventilation is required to ensure optimal result. Product can be dried with or without oven.
Application	<p>Stir the lacquer carefully before use. Avoid flotation.</p> <p>For airless spraying, the product is thinned approximately 0–5% to the viscosity 45–65s (DIN4). Recommended nozzle tip is 0.011"–0.015" and pressure 80–160 bar. Spray angle shall be chosen according to the shape of the object.</p> <p>For air–assisted airless spraying, the product is thinned approximately 0–5% to the viscosity 45–65s (DIN4). Recommended nozzle tip is 0.011"–0.015" and pressure 40–120 bar. Atomising air pressure should be about 1–3 bar. Spray angle shall be chosen according to the shape of the object.</p> <p>For conventional spraying, the product is thinned approximately 0–5% to the viscosity 45–60s (DIN4). Recommended nozzle tip is 1.4–1.8 mm and pressure 2–3 bar.</p> <p>For curtain coating, the product is thinned approximately 0–5% to the viscosity 50–60s (DIN4). Avoid too high pumping pressure and flowing speed.</p>
Thinners	Water, Akvi Thinner
Cleaning of equipment	Water.
VOC	The Volatile Organic Compounds amount is 129 g/litre of paint mixture. VOC content of the paint mixture (thinned 5% by volume) is 123 g/l. VOC 2004/42/EC (cat A/e) 130 g/l (2010)

HEALTH AND SAFETY Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets.

A health and safety data sheet is available on request from Tikkurila Oyj.

For industrial and professional use only.

The above information is not intended to be exhaustive or complete. The information is based on laboratory tests and practical experience, and it is given to the best of our knowledge. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As manufacturer we cannot control the conditions under which the product is being used or the many factors that have an effect on the use and application of the product. We disclaim liability for any damages caused by using the product against our instructions or for inappropriate purposes. We reserve the right to change the given information unilaterally without notice.

The product is intended for professional use only and shall only be used by professionals who have sufficient knowledge and expertise on the proper use of the product. The information above is advisory only. To the extent permitted by applicable law, we shall not approve of any liability for the conditions under which the product is being used or for the use or application of the product.

In case you intend to use the product for any other purpose than that recommended in this document without first getting our written confirmation on the suitability for the intended use, such use takes place at your own risk.